



## GENERAL PRODUCT SPECIFICATION

<b>Item No.</b>	<b>GP152-P-E</b>
-----------------	------------------

<b>Date</b>	16-6-2017	<b>Replaces</b>	1-10-2014	<b>No. Pages</b>	1
-------------	-----------	-----------------	-----------	------------------	---

### Product Description:

<b>Style</b>	Blanket roll
<b>Item Size (each)</b>	48 cm x 44 m
<b>Color</b>	Gray
<b>Composition</b>	Polypropylene >98%, Surfactant < 1.0%, color pigment < 1.0 %
<b>Structure</b>	A nonwoven mat of randomly oriented Micro-fibers [2-10 micron diameters]
<b>Technology</b>	Meltblown
<b>Absorbency</b>	Universal ( <b>Hydrophilic</b> + Oleophilic)
<b>Bonding</b>	Bonded (staggered pattern) + Mechanical entanglement

<b>Intended Application</b>	Chemical Resistant Sorbent for Water, Oil, or Solvent Base Liquids
-----------------------------	--

<b>Absorbency Capacity</b>	192 l per bale (saturated; medium viscosity-14x)
----------------------------	--

### Packaging Description:

Package configuration	Bale	Pkg. Weight	12.0 kg (11.8kg)
Items per Package	2 Blanket Roll/Bale	Pkg. Dimensions	43cm x 43cm x 98cm (H)
Container type	Polybag + Twist tie		

### Physical Properties;

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
Basis Weight	SPCTM-002A	G/M2	280	28
Caliper	SPCTM-020	mm	4.6	0.4
Absorbency ** (med. Oil)	SPCTM-004B	gL/gS	14	2
Tensile strength	SPCTM-007	daN	6.3	0.6
Color	Visual	-----	Gray	per standard

**The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.**

**\*\* The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

<b>Attributes</b>	Product will be free of foreign material contamination, rips, holes, and tears.
<b>Labeling</b>	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
<b>Certification</b>	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.